



STATE OF THE PROPERTY OF THE P

MICROCOPY RESOLUTION TEST CHART

# FOREIGN TECHNOLOGY DIVISION



A NEW MATERIAL WITH GREAT PROSPECT -- RAPIDLY SOLIDIFIED MICROCRYSTAL MATERIAL

bу

Shi-Xun Zhang



IIC FILE COPY



Approved for public release; Distribution unlimited.

# EDITED TRANSLATION

FTD-ID(RS)T-1155-85

17 Mar 86

MICROFICHE NR: FTD-86-C-001632

A NEW MATERIAL WITH GREAT PROSPECT -- RAPIDLY SOLIDIFIED MICROCRYSTAL MATERIAL

By: Shi-Xun Zhang

English pages: 3

Source: Jin Shu Re Chu Li, Nr. 1(Nr. 77), 1984, pp. 15-16

Country of origin: China Translated by: SCITRAN

F33657-84-D-0165

Requester: FTD/TQTA

Approved for public release; Distribution unlimited.

THIS TRANSLATION IS A RENDITION OF THE ORIGINAL FOREIGN TEXT WITHOUT ANY ANALYTICAL OR EDITORIAL COMMENT. STATEMENTS OR THEORIES ADVOCATED OR IMPLIED ARE THOSE OF THE SOURCE AND DO NOT NECESSARILY REFLECT THE POSITION OR OPINION OF THE FOREIGN TECHNOLOGY DIVISION

PREPARED BY:

TRANSLATION DIVISION FOREIGN TECHNOLOGY DIVISION WP-AFB, OHIO.

### GRAPHICS DISCLAIMER

All figures, graphics, tables, equations, etc. merged into this translation were extracted from the best quality copy available.

n For		
CRA&I	1	
TAB		
punced		
ation	<b></b>	
ution /	Codes	
	CRA&I TAB purced ation ution / vailability	CRA&I TAB Dunced Dation

3 2

## A New Material With Great Prospect --Rapidly Solidified Microcrystal Material

Shi-Xun Zhang, Engineering College of Southern China

Rapidly solidified materials have been developed for the last decade. Due to its excellent properties, this material had gained attention from the scientists and engineers in many countries. Its theoretical basis and practical applications have been under investigation thoroughly and broadly.

The cooling rate of the metal materials which are manufactured in industry by ordinary techniques is about  $10^{-2} \sim 10^{2}$  °C/s (The cooling rate of some powder metallurgy can reach  $10^{3} \sim 10^{4}$  °C/s). In general, when we say rapid solidification, we mean the cooling rate is higher than  $10^{2}$  °C/s. Right now the cooling rate of the rapidly solidified technique which is often used in foreign countries is in the range of  $10^{5} \sim 10^{6}$  °C/s. The products made by this technique include rapidly solidified single- or double-rolled thin plate, ultrasonic foggy powder, rapidly rotating electrode powder, etc. The rapidly solidified materials can be divided into two kinds: amorphous metal material (i.e. metal glass) and microcrystal metal material.

material are: \$1) It has a very fine and homogeneous structure. When the cooling rate is 10 - 10 c/s, the size of the crystal grain is about 0.5 to a few mm. Its partial resolution is very small. The range of the partial resolution, and the distance between each crystal branch arm is about 0.5 - 5 mm. As the cooling rate increases, the

crystal grain can be further refined and the partial resolution can be further reduced or even eliminated. Because of the very fine and homogeneous structure, the microcrystal material has very good mechanical properties. Compared with ordinary materials, its strength and ductility, stress and corrosion resistance, fatigue fracture resistance, and high temperature oxidization resistance are much higher. 7(2) The solid solubility is enhanced remarkably. Due to the high cooling rate, the solid solubility of the rapidly solidified materials can be increased remarkably. Let's take Al alloy as an example. At 934°K, the equilibrious solid solubility of Cu in Al is he rapid solidification 0.44%, but it is as high as 17-18 technique is employed. Therefore by using this technique, we not only can obtain a high strength material, but more importantly we also can add some metal elements into the metal alloys. These metal alloys which have some special properties can not be obtained by ordinary techniques. If  $3\sim4\%$  of Li, for example, is added into the Al-Cu alloy, its strength and ductility can be enhanced remarkably. However, if this alloy is made by ordinary techniques, it will become brittle because of the existence of Li.

[]:

so far there have been some rapidly solidified microcrystal materials which are used practically and experimentally in foreign countries. They are high speed steel, high temperature alloy, stainless steel, and Al alloy. In the process of rapid solidification, the foggy powders or thin plates are usually made first. After that, these powders or thin plates are then pressed into high density materials by the method of thermal-equilibrium-static pressing or thermal pressing.

Since the rapidly solidified materials have such excellent properties, many material scientists believe that the rapid solidification technique could open a new frontier for material science. This new technique will make the development of new alloys and special materials which can not be made by ordinary techniques possible. It should thus have great prospects and high potential.

# EMED

5-86